



## PILOCEM (EN 998-1:2003)



**ADVANCE BUILDING INDUSTRIES**  
Borg El Arab –Industrial Zone – Phase 4  
P.O. BOX 158  
Alexandria – Egypt

**09**

### **EN 998-1**

**General Purpose rendering / plastering mortar (GP) for external and internal use CSIII**

Reaction to fire: Class A1

Adhesion: 0,25 N/mm<sup>2</sup>

Water absorption: W1

Water vapour diffusion coeff.:  $\mu$  15/35 (tab. value)

Thermal conductivity ( $\lambda_{10, dry}$ ): P = 50%  $\lambda = 0,83$  W/mK (tab. values)

P = 90%  $\lambda = 0,93$  W/mK

Durability: (against freeze/thaw): excellent (evaluation based on provisions valid indented place of use of the mortar)

Dangerous Substances: See technical data and related marking

CYPRUS: Head Office: Michali Zeipekki 23, 4525 Moni - Limassol, Cyprus. Tel: +357 25632642, Fax: +357 25632091, E-mail: [zeiplast@zeiplast.com](mailto:zeiplast@zeiplast.com)

EGYPT: A.B.I. Borg El-Arab, Alexandria, Egypt, Industrial Zone, Phase 4. Tel: +203 4595967/8/9, Fax: +203 4595971, E-mail: [adbuilding\\_eg@yahoo.com](mailto:adbuilding_eg@yahoo.com)

SAUDI ARABIA: P.M.I. Al Khumrah Industrial Area, Jeddah, Saudi Arabia. Tel/Fax: +966 266 29901/2/3, E-mail: [pmisaied@yahoo.com](mailto:pmisaied@yahoo.com)

UAE: Zeiplast Emirates. Delma St., Abu Dhabi, U.A.E P.O.Box 42591. Tel: +971 24 456789, Fax: +971 24 456788 E-mail: [zeiplast@eim.ae](mailto:zeiplast@eim.ae)